

TEST REPORT

REPORT NUMBER : TURT190158409
APPLICANT NAME : Hnc Yapı Dekorasyon San.Tic.Ltd.Şti.
ADDRESS : Atatürk Bulv. İmç Blokları 2.Blok No:2518 Fatih İstanbul / TURKEY
TEL:0212 512 05 10FAX:0212 512 05 11
Attention : Cem Şahin (cem@hncyapi.com)
SAMPLE DESCRIPTION : One sample of white/lilac allover printed woven fabric with coated
DATE IN : 4 September ,2019 (13:43:00)
DATE OUT : 6 September ,2019
BUYER : Not Given
REFERENCE : FABRIC BACKED WALLCOVERING
FIBER COMPOSITION : Not Given
NOTE : Test method was given by the applicant.
PROVIDED CARE LABEL : Not Given

TEST	SAMPLE
Colour Fastness to Light	1 NR

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE / LS = LACK OF SAMPLE / NC = NO COMMENT / I = INCONCLUSIVE / # = SEE RESULT / NF = NEEDS FURTHER TESTING / A = ABSENT / M = MARGINAL ACCEPT / SD = SEE DETAILS ENCLOSED / FS = FURTHER STEPS / P* = COMMERCIALY ACCEPTED BY CLIENT

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Opinions and interpretations expressed herein are outside the scope of TÜRKAK accreditation. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory.



Gülçin ÇETİN
Customer Care Executive



Nida ARSLANBAY
Textile Laboratory Manager

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna-34197 /ISTANBUL
Phone : +90 212 496 46 46 Fax: +90 212 452 80 55
e-mail : intertekcg.turkiye@intertek.com
<http://www.intertek-turkey.com>



190158409

Test Method	Results	Requirements
-------------	---------	--------------

Colour Fastness to Light

AATCC 16.3 : 2014

40 AFU

Equipment: Atlas CI 4000

Equipment type: Water cooled

Lamp type: Xenon-Arc Lamp

Black Panel Temperature: 63±1°C

Chamber air temperature: 43±2°C

Irradiance: 1.10 W/m²/nm at 420 nm

Exposure controlled by: AATCC Blue Wool

Water Type: Demineralized

One specimen is tested unless otherwise is requested.

Shade Change

	2.5	No Requirement
--	-----	----------------

END OF TEST REPORT